

E-PASTE 1050

modelling paste

jun.2021

For production of seamless models, contour shaped machinable blanks, mock-ups, composite toolings; good adhesion on expanded polystyrene and wood; good behavior on vertical supports up to 25 mm

Property	Value	Test method
Colour (of mixed components)	brown	
Mixing ratio (by weight)	A : B = 100 : 50	
Working time at 20°C (150 g)	30-40 minutes	
Setting time at 23°C and thickness 20 mm	12 h	
Density at 20°C	0,60-0,62 g/cm ³	ISO 845
Cured hardness	55 Shore D	ISO 868
Compressive strength	30-35 MPa	ISO 604

Packaging:

Comp A 12 kg, 120 kg

Comp B 6 kg, 120 kg

The information and recommendations contained herein are based on our research and are believed to be accurate, but no warranty, express or implied, is made or should be inferred. Purchasers should test the products to determine acceptable quality and suitability for their own intended use. Nothing contained herein shall be construed to imply the nonexistence of any relevant patents or to constitute a permission, inducement or recommendation to practice any invention covered by any patent, without authority from the owner of the patent.



SAMSON KAMNIK d.o.o. Kovinarska cesta 28, SI-1240 KAMNIK, SLOVENIJA

Tel: 00386 1 83 17 255, 01 83 19 260 Fax: 00386 1 83 17 179 samson@samson-kamnik.si www.samson-kamnik.si
www.revivo.si www.naravno.info www.kompoziti.si www.naredi.eu